

TAIUREX[®] HIPS HP9450

Category :High Impact Polystyrene(HIPS)

Property	Unit	Test Method	Test Condition	High Impact PS HP9450
Tensile Strength	kg/cm ² (MPa)	ASTM D-638	23 °C	250 (25)
Tensile Modulus	kg/cm ² X104 (MPa)	ASTM D-638	23 °C	2.2 (2160)
Tensile Elongation	%	ASTM D-638	23 °C	52
Flexural Strength	kg/cm ² (MPa)	ASTM D-790	23 °C	470 (46)
Flexural Modulus	kg/cm ² X104 (MPa)	ASTM D-790	23 °C	2.2 (2160)
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23 °C 1/4" bar	15 (147)
Vicat Softening Point	°C	ASTM D-1525	Annealed 80°C ×2hr 1/8" bar	100
Heat Deflection Temperature	°C	ASTM D-648	Annealed 80°C ×2hr 1/8" bar	90
Melt Flow Index		ASTM D-1238	200°C ×5Kg(49N)	3.0
Reidual Monomer	ppm max.			700
Specific Gravity		ASTM D-792	23 °C	1.04
Flammability		UL-94	File No. E162823	1.5-1.7mm HB All Color
Characteristics	Super high impact			

Contact Jiaxing Fulltrust Plastic Co.,Ltd.

Website:www.fulltrustplastic.com

Email : jerry@fulltrustplastic.com

Mobile& Whats'app : +86 18657312116

Address : No.100 Zhuyuan Road , Nanhu District, Jiaxing City,China